EAST Search History

EAST Search History (Prior Art)

Ref #	Hits	Search Query	DBs	Default Operator	Plurals	Time Stamp
L1	0	green adj foam and slurry with (fired sintered heated) and foam with stretched	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/12/17 13:59
L2	1	foam with slurry with (fired sintered heated) and foam with stretched and ceramic	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/12/17 13:59
L3	53	"254557"	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/12/17 14:00
L4	1	slurry with (fired sintered heated) and foam with stretched and ceramic	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/12/17 14:15
L5	10	slurry with (fired sintered heated) and (pores voids cells) with (major minor) adj axis and ceramic	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/12/17 14:16
L6	1	foam with slurry with (fired sintered heated) and (pores voids cells) with (major minor) adj axis and ceramic	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/12/17 14:17

L7	0	foam with slurry with (fired sintered heated) and (pores voids cells) with elongate$1 and ceramic	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/12/17 14:17
L8	14	foam with slurry with (fired sintered heated) and (pores voids cells) with ratio and ceramic	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/12/17 14:17
L9	4	foam with slurry with (fired sintered heated) and (pores voids cells) with (length diameter aspect) with ratio and ceramic	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/12/17 14:20
L10	1	foam with slurry with (fired sintered heated) and (pores voids cells) with oriented and ceramic	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/12/17 14:22
L11	5	foam with slurry with (fired sintered heated) and (pores voids cells) and ceramic and nippondenso	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/12/17 14:24
L12	0	foam with slurry with (fired sintered heated) and (pores voids cells) with microns and ceramic and nippondenso	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/12/17 14:26
L13	0	foam with slurry with (fired sintered heated) and (pores voids cells) with micrometers and ceramic and nippondenso	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/12/17 14:27

L14	6	foam with slurry with (fired sintered heated) and (pores voids cells) with micrometers and ceramic	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/12/17 14:27
L15	0	foam with slurry with (fired sintered heated) and (pores voids cells) with micrometers and ceramic and stretched	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/12/17 14:27
L16	0	foam with slurry with (fired sintered heated) and (pores voids cells) with micrometers and ceramic and stretching	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/12/17 14:27
L17	2	foam with slurry with (fired sintered heated) and (pores voids cells) and ceramic and stretching	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/12/17 14:27
L18	2	foam with slurry with (fired sintered heated) and (pores voids cells) and ceramic and stretch $3	US-PGPUB; USPAT; USOCR; FPRS; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2009/12/17 14:27

EAST Search History (Interference)

< This search history is empty>

12/17/2009 2:28:21 PM
C:\ Documents and Settings\ hvo2\ My Documents\ EAST\ Workspaces\ default.wsp